



EZ ELECTROSTATIC UNIVERSAL PRIMER 1169 GRAY 0866 RED OXIDE

EZ Electrostatic Universal Primer is a universal heavy duty rust inhibitive primer that can be topcoated with most paints, including epoxies and urethanes.

This product was formulated to spray with electrostatic equipment without any adjustments to the paint.

EZ Electrostatic Universal Primer can also be used as a barrier coat between previously painted surfaces and topcoats containing strong solvents.

Ordering:

Available in single gallons.

Technical Data

Type: Phenolic Modified Alkyd

Components: One

Colors: Gray and Red Oxide

Gloss: Flat

V.O.C: 3.4 lbs. per gallon \pm .2 Lbs.

Solids by Volume: 52 % \pm 2 %

Flash Point: 45° F.

Shelf Life: 1 year

Temperature Resistance: 200° F. Max.

Recommended Film Thickness: 2 - 2.5 dry film

Spreading Rate: 810 sq. ft. per gal. @ 1 mil,
324-405 sq. ft. per gal. @ recommended dft.

Pot Life: N/A

EZ Electrostatic Universal Primer is used for:

- Ornamental Iron
- Structural Steel
- Misc. Metals
- Tanks
- General Maintenance
- Process Equipment

Surface Preparation: Surface must be clean, dry, and free from any contaminants including oil, grease, dirt, loose rust, loose paint, or loose mill scale. This product performs well over surfaces cleaned according to SSPC-SP-3 Power Tool Cleaning. In severely corrosive environments, SSPC-SP-6 Commercial Blast is recommended. **Note:** Excessive film or surface contamination may cause adhesion problems. If surface is sandblasted, it must be coated within 8 hours to avoid early rusting.

Mixing: Stir thoroughly prior to use.

Dry Time: To Touch: 20 minutes
Tack Free: 40 minutes
Re-coat: 2 hours.

Application: Electrostatic, Conventional or Airless Spray Equipment.

Thinning: Thinning not normally required. If thinning is desired, use Sumter Coatings 560X1005 Reducer.

Clean-up: Sumter Coatings 560X1005