

**W/R SURE GRIP (PFGA) BLACK
196N1306**

W/R SURE-GRIP (PFGA) was formulated using latest water-borne technology that makes this product ideal for use over **Galvanize and Aluminum substrates**. W/R Sure Grip provides excellent adhesion and a super hard finish almost immediately. Even though Sure Grip was formulated for Galvanize and Aluminum, it is also a great paint for Hot-Dipped or Cold Rolled Steel.

When painting over new galvanized metal that is very shiny in appearance, it will be important to test for adhesion. This can be done by applying a small amount of paint on the surface and allowing to dry for approximately 72 hrs. Next, make a cross (X) cut in the paint film, and apply tape over the cut. Press down firmly to assure that tape adheres to the paint and then in one swift motion, pull the tape from the paint. If adhesion is poor, most of the paint between the cuts will be removed. If this happens, consult the manufacturer for further instructions.

Technical Data

Type: Water Reducible

Components: One

Colors: Black

Gloss: 15 – 25%

V.O.C.: 1.2 lbs. per gallon

Solids by Volume: 35% ± 2%

Flash Point: N/A

Shelf Life: 6 months

Temperature Resistance: 250° F

**W/R SURE GRIP (PFGA)
CAN BE USED FOR:**

- Ornamental Iron • Window Extrusions •
- Industrial Equipment •Patio Furniture •
- Sheet Metal • and Many Other Uses •

Ordering:

Available in gallon cans.

Surface Preparation: Remove all contaminants including oil, grease, loose paint, dirt or any other contaminants. SSPC-SP3 Power Tool Cleaning can aid in assuring optimum adhesion.

Mixing: Stir thoroughly prior to use.

Recommended Film Thickness: 1.0 - 2.0 mils dry film.

Spreading Rate: Theoretical 560 sq. ft. per gal. @ 1 dry mil.

Pot Life: N/A

Dry Time: @ 77° F.

To Touch: 15 - 25 minutes

Tack Free: 35 - 45 minutes

Dry Hard: 16 hours

Application: Conventional, Airless or HVLP Spray systems. Brush for touch-up only.

Thinning: Water

Clean-up: Warm Water