

**No. 5 Tank Enamel
(880W2203)**

No. 5 Tank Enamel, developed to provide our customers an economical paint system that adds years to the life of their equipment. The finest alkyds are used combined with maximum pigment levels to ensure great coverage and optimum hiding power.

No. 5 Tank Enamel is used for: LP Gas Tanks and Cylinders, Bulk Storage Tanks, Storage Buildings and Stores.

Technical Data

Type: Alkyd

Components: one

Colors: Blued White, Mist Gray, Baby Blue, Tan, Ivory, Rural Green, Light Green. Special colors available upon request.

Gloss: 85° minimum

Solids by Volume: 48% + or - 2%

Spreading Rate: 786 sq. ft. per gal. @ 1 mil dft; 318 - 524 sq. ft. per gal. @ recommended dft.

Recommended Film Thickness: 1.5 - 2.5 dry film

Shelf Life: 1 year

V.O.C.: max. 3.8 lb/gal or 455 gr./lt.
Theoretical unreduced - 3.3 lb/gal

Flash Point: 100° F.

Temperature Resistance: 225° F.

5 Reasons to use No. 5 Tank Enamel

- Extended Durability
- Excellent Hiding Power
- Ease of Application
- Enhanced Gloss
- Economical

Ordering:

Available in single gallons and five gallon pails.

Recommended Primer: Uni-Pox Primer-855W1370 (OffWhite) or 855G1368 (Gray-Green).

Mixing: Stir thoroughly prior to use.

Pot Life: N/A

Surface Preparation: Surface should be free of dirt, oil, grease, loose rust, loose mill scale, and any other contaminants. Recommended removal is SSPC-SP3 Power Tool Cleaning.

Application: Preferred - Roll using ½" or ¾" lambswool or synthetic cover. Brushing is also optional. Conventional or airless spray equipment can be used, thin up to 5 %.

Dry Time: @ 77° F.

To Touch: 1 hour
Tack Free: 8-12 hours
Re-coat: 24 hours

Thinning: For spray application only: as necessary, up to 5 % with XL Thinner (856X2210) or Mineral Spirits.

Clean-up: XL Thinner or Mineral Spirits

9/99