

**No. 7 Silicone Alkyd Enamel  
(880W2201)**

**No. 7 Silicone Alkyd** is a premium alkyd that has been modified with a high percentage of silicone to create a product that will perform for many years, when used properly. **No. 7 Silicone Alkyd** is the preferred product when a long-lasting finish is a must. Gloss and color retention on this product is excellent, compared to most single package products.

**Technical Data**

**Type:** Silicone Modified Alkyd

**Components:** One

**Colors:** White, special colors available upon request.

**Gloss:** 90°

**V.O.C:** max. 3.8 LB/gal or 455 gr./lt.  
Theoretical unreduced 3.5 lb/gal

**Solids by Volume:** 50% + or - 2%

**Flash Point:** 100° F.

**Shelf Life:** 1 year

**Temperature Resistance:**  
Max. 300° F. Continuous  
Max. 400° F. Intermittent

**Surface Preparation:** Minimum SSPC-SP-6. Remove all contaminants including oil, grease, dirt, loose mill scale, and rust. Prime with recommended primer.

**7 Reasons to use No. 7**

- High Gloss
- Long Coating Life
- Non - Chalking
- User Friendly
- Excellent Color Retention
- Paint Reduction
- Lead & Chrome Free

**Ordering:** Available in single gallons and five gallon pails

**Application:** Brush, roll, or spray. Use synthetic or lambswool roller cover.

**Recommended Primer:** Uni-Pox Primer – 855W1370 (Off White) or 855G1368 (Gray-Green).

**Mixing:** Stir thoroughly prior use.

**Recommended Film Thickness:** 1.5 - 2.5 mils dry film.

**Spreading Rate:** 800 sq. ft per gal. @ 1 mil.  
320 - 530 sq. ft. per gal. @ recommended dft.

**Pot Life:** N/A

**Dry Time:** @ 77° F.  
To Touch: 2 hours  
Tack Free: 4 hours  
Re-coat: Overnight

**Thinning:** For spray application, up to 5% with XL Thinner (856X2210) or Mineral Spirits. Thinning not required for brushing or rolling.

**Clean-up:** XL Thinner, Mineral Spirits or Xylene.

9/99